

TEIRA Flat Elements and Corners Units: mm



Given the characteristics of aggregates and their photographic reproduction, there may be slight variations in particle size and tone.



Product characteristics and package			Technical Specifications		
Colors Available	T 08	T 46	T 47	Product Classification	EN 14618 Concrete Coating
Product Type	Flat Elements	Corners	Surface Quality	EN 14617-16	Visual Inspection
Quantity per Pallet	18 sqm	45 lm	Dimensions and Geometry	EN 14617-16	Tolerances \pm 5 mm
Quantity per Box	0,60 sqm	1,50 lm	Maximum Water Absorption	EN 14617-1	\leq 10 %
Boxes/Pallet	30 Boxes	30 Boxes	Average Apparent Density	EN 14617-1	1700 \pm 50kg/m ³
Average weight/sqm	50 kg	20,7 kg	Freeze/Thaw Resistance Flexural Strength (after 25 cycles)	EN 14617-5 EN 14617-2	Pass No change
Average weight/Box	30 kg	27 kg	Thermal Shock Resistance Flexural Strength (after 20 cycles)	EN 14617-6 EN 14617-2	Pass No change
Average weight/Pallet	954 kg With Pallet	962 kg With Pallet	Minimum Flexural Strength	EN 14617-2	6 MPa
			Compressive Strength Class Minimum Compressive Strength	EN 206 EN 12390-3	LC30/33 \geq 33 N/mm ²
			Water Absorption by Capillary	EN 772-11	\leq 1 g/(m ² .s)
Approved: Vitor Silva	Elaborate: Bruno Veloso	PTDS n^o: TEI_001_EN	Date: 09-03-2020		